



Specialty Flooring Products

www.nikkacorp.com | (678) 290-0830

TECHNICAL DATA: EPOXY CRACK FILLER

EPOXY CRACK FILLER

NC- Epoxy Crack Filler (NC-ECF) is a two component 100% solids epoxy crack filler designed for shallow repair on either vertical or horizontal surfaces. This product is easy to mix and use and has a non-critical mix ratio.

RECOMMENDED USES

Recommended for repairing cracks and defects in concrete or masonry.

GENERAL PRODUCT DATA

SOLIDS BY WEIGHT:

100%

SOLIDS BY VOLUME:

100%

VOLATILE ORGANIC CONTENT:

Zero pounds per gallon

MIX RATIO:

1 part A to 1 part B by volume

RECOMMENDED FILM THICKNESS:

1/8" cracks or thin build repairs

COVERAGE PER GALLON:

0.13 cubic feet or 1,228 lineal feet @ 1/8" x 1/8"

COLORS AVAILABLE:

Gray (when mixed)

SHELF LIFE:

6 months in unopened containers

PACKAGING INFORMATION

2 gallon kit= 1 gallon part A @ 11.1 pounds and 1 gallon part B @ 11.2 pounds (22.3 pounds net)

10 gallon kits (111.5 pounds net) (volumes and weights approximate)

HARDNESS:

Shore D = 65

IMPACT RESISTANCE:

Gardner Impact, direct = 50 in. lb. (passed)

COMPRESSIVE STRENGTH:

8,710 psi @ ASTM D695

TENSILE STRENGTH:

6,256 psi @ ASTM D638

FLEXURAL STRENGTH:

7,500 psi @ ASTM D790

ABRASION RESISTANCE:

Taber abraser CS-17 calibrase wheel with 1000 gram total load and 500 cycles = 36 mg loss

ADHESION:

350 psi @ elcometer (concrete failure, no delamination)

VISCOSITY:

Mixed = > 3,100,000 cps (typical)

ULTIMATE ELONGATION:

2.4%

DOT CLASSIFICATIONS:

Part A "not regulated"

Part B "CORROSIVE LIQUID N.O.S., 8, UN11760, PGIII"

HEAT DEFLECTION TEMP.:

59 degrees C (138 degrees F)

CURE SCHEDULE (70°):

Pot life – 2 gallon volume 1-3 hours
Tack free (dry to touch)..... 5-10 hours
Recoat or topcoat.....immediately after application
Light foot traffic.....10-24 hours
Full cure (heavy traffic).....2-7 days

APPLICATION TEMPERATURE:

60-90 degrees F

CHEMICAL RESISTANCE:

REAGENT	RATING
butanol	3
xylene	2
1,1,1 trichloroethane	1
MEK	1
methanol	1
ethyl alcohol	1
skydrol	2
10% sodium hydroxide	5
50% sodium hydroxide	4
10% sulfuric acid	3
70% sulfuric acid	1
10% HCl (aq)	3
5% acetic acid	1

Rating key: 1 - not recommended, 2 - 2 hour term splash spill, 3 - 8 hour term splash spill, 4 - 72 hour immersion, 5 - long term immersion. NOTE: Extensive chemical resistance information is available through your sales representative.

PRIMER:

None necessary

TOPCOAT:

Optional: This product can be overcoated with many suitable epoxy and urethane products.

LIMITATIONS:

- *Color stability may be affected by environmental conditions such as high humidity, chemical exposure, or exposure to certain types of lighting such as sodium vapor lights.
- *Colors may vary from batch to batch.
- *This product is not UV color stable and may discolor when exposed to UV light sources.
- *Substrate temperature must be 5°F above dew point.
- *All new concrete must be cured for at least 30 days prior to application.
- *Many epoxy products can be placed directly over the uncured epoxy crack filler immediately after the material is used provided that the cracks are small.
- *See reverse side for application instructions.
- *Physical properties are typical values and not specifications.
- *See reverse side for limitations of our liability and warranty.

EPOXY CRACK FILLER

MIXING AND APPLICATION INSTRUCTIONS

PRODUCT STORAGE: Store product at normal room temperature before using. Continuous storage should be between 60 and 90 degree F. Low temperatures or temperature fluctuations may cause product crystallization.

SURFACE PREPARATION: All dirt, foreign contaminants, oil and laitance must be removed to assure a trouble free bond to the substrate. A test should be made to determine that the concrete is dry; this can be done by placing a 4'X4' plastic sheet and taping down the edges. If after 24 hours, the substrate is still dry below the plastic sheet then the substrate is dry enough to start repair work. This product is intended for hairline cracks and other fractures up to an 1/8 inch in width. Remove all unsound concrete from within the crack to be repaired and thoroughly vacuum all debris and dust from within the crack opening. For applications directly over concrete, Testing should be performed to confirm a moisture vapor emission rate below 3 lb/24hr/1000 ft² per ASTM F1869

PRODUCT MIXING: This product has a mix ratio of 1 part A to 1 part B by volume. To mix, simply measure out equal volumes of the material and mix them together thoroughly with slow speed mixing equipment such as a jiffy mixer, putty knife or spatula until the material is thoroughly mixed and uniform in color. Mix only an amount of material that can be used in the allotted pot life period. Improper or insufficient mixing may result in product failure.

PRIMING: No priming is necessary.

PRODUCT APPLICATION: The mixed material can be applied by marginal trowel, putty knife or any other suitable equipment.

RECOAT OR TOPCOATING: When repairing cracks that are less than 1/8" thickness, many epoxies can be placed directly over the applied crack filler before it is cured. Alternatively, it is also acceptable to allow the material to cure before installing the coating. If excessive amounts are spread well beyond the crack repair or in an areas where surface repairs have been implemented, it is best to check the cured areas for any possible amine blush (a whitish, greasy film or deglossing) prior to coating over this material. If a blush is present, it can be removed by any standard type detergent cleaner prior to topcoating or recoating. Many epoxy coatings and urethanes are compatible for use over this product as well as multiple coats of this product.

CLEANUP: Use xylol.

FLOOR CLEANING: Caution! Some cleaners may affect the color of the fast set gel installed. Test each cleaner in a small area, utilizing your cleaning technique. If no ill effects are noted, you can continue to clean with the product and process tested.

RESTRICTIONS: Restrict the use of the floor to light traffic and non-harsh chemicals until the coating is fully cured (see technical data under full cure). It is best to let the floor remain dry for the full cure cycle.

Warranty

Since no control is exercised over product use, The Nikka Corporation warrants that its products are manufactured free from defect and are consistent and within manufacturing tolerances on our data sheets. No other oral or written representation or statement of any kind, expressed or implied, now or hereafter made is authorized or warranted by The Nikka Corporation. This product is supplied on the condition that you shall make your own tests to determine the suitability of our product for your particular use. The Nikka Corporation shall have no liability for incidental or consequential damage, direct or indirect. Our liability is limited to price of or replacement of our product at our option. By accepting delivery of our product means that you have accepted the terms of The Nikka Corporation Warranty.

Nikka Corporation
1880 West Oak Pkwy, Ste. 110
Marietta, GA 30066
678-290-0838
www.nikkacorp.com